

TOOL STEELS - PLASTIC MOULDING STEEL SOLUTIONS

	INDUSTEEL	DIN	W.Nr	AISI	CHEMICAL COMPOSITION IN %					DELIVERY CONDITION		MANUFACTURING PROGRAMME				USAGE	
					C	Ni	Cr	Mo	Mn	Others	Hardness HB	Hardness HRC	Thickness range		Width		
													mm	inches	mm	inches	
MOULDS CORES & CAVITIES	4140	42 CrMo 4	1.7225	4140	0.41	-	1.00	0.20	0.06	V	258-302	26-32	7-135	0.27-5.3	1000-3500	39.3-137.9	Mechanical Engineering Cores and cavities with high requirements in homogeneity, surface finish, machining.
	2311	40 CrMnMo 7	1.2311	P20	0.40	-	1.90	0.20	-		280-325	29-34	7-610	0.27-24.0	1000-2500	39.3-98.4	
	2738	40 CrMnNiMo 8-6-4	1.2738	P20 + Ni	0.40	1.00	1.90	0.20	1.5		280-325	29-34	7-610	0.27-24.0	1000-2500	39.3-98.4	
	2767		1.2767	6F7	0.45	3.90	1.30	-	-		260	26.5	15-350	0.59-13.8	1000-3000	39.3-82.7	
	Superplast® 300		1.2738 mod	P20 mod	0.26	0.30	1.40	0.45	1.4	B	290-330	30-35	15-900	0.59-35.4	1000-2500	39.3-98.4	
	Superplast® 350		1.2738 mod HH	P20 mod HH	0.26	0.30	1.60	0.65	1.5	B	330-360	35-39	15-900	0.59-35.4	1000-2500	39.3-98.4	
	2714+S	55 NiCrMoV 7			0.55	1.70	1.10	0.50	0.9	V, S:0.07	360-400	39-43	8-320	0.31-12.6	1000-2500	39.3-98.4	
	Superplast® 400				0.25	0.75	2.00	0.60	1.15	B,V	350-380	38-42	15-610	0.59-24.0	1000-2500	39.3-98.4	
	Superplast® Premium				0.26	+	1.60-2.00	0.65	1.3	B	290-380	30-42	200-610	7.87-24.0	1000-2100	39.3-82.7	
MOULDS BASES & HOT RUNNERS	4130	30CrMo 4	1.7225	4130	0.30	-	1.00	0.16	-		258-302	26-32	7-135	0.27-5.3	1000-3500	39.3-137.9	Cores and cavities with basic requirements
	2312	40 CrMnMoS 8-6	1.2312	P-20 +S	0.40	-	1.90	0.20	1.5	S: 0.06	280-325	29-34	7-610	0.27-24.0	1000-2500	39.3-98.4	
	2714	55 NiCrMoV 7	1.2714	L6	0.55	1.70	1.10	0.50	0.9	V	360-400	39-43	8-120	0.31-4.7	1000-2500	39.3-98.4	
CORROSION-RESISTANT MOULDS	2083	X 42 Cr 13	1.2083	420	0.40	-	13.00	-	0.6		280-310	29-33	15-130	0.59-5.1	1000-3500	39.3-137.9	Stainless cores and cavities
	2316	X 36 CrMo 17	1.2316		0.40	-	16.00	1.03	0.9		280-325	29-34	15-225	0.59-8.9	1000-3500	39.3-137.9	
	2085	X 33 CrS 16	1.2085	420F mod	0.33	-	16.00	-	1.1	S: 0.07	280-325	29-34	15-350	0.59-13.8	1000-3500	39.3-137.9	Corrosion-resistant holders and support plates
	2316+S			420F mod	0.40	-	16.00	1.03	0.9	S: 0.07	280-325	29-34	15-300	0.59-11.8	1000-2500	39.3-98.4	
	Superplast® Stainless		1.2099		0.07	0.50	12.00	-	1.4	S: 0.12	290-330	30-35	15-350	0.59-13.8	1000-2000	39.3-78.7	

Other properties can be studied by the mill on request. Industeel reserves the right to modify above data.

Contact Marketing : +33 3 85 80 52 56  
 Contact Sales : +33 4 77 75 21 29  
 Fax : +33 3 85 80 55 00  
<http://industeel.arcelormittal.com>

TOOL STEELS - COLD & HOT WORK TOOL STEELS

INDUSTEEL
EURONORMS
W.Nr
AIISI
JIS
CHEMICAL COMPOSITION IN %
DELIVERY CONDITION
MANUFACTURING PROGRAMME
USAGE

	INDUSTEEL	EURONORMS	W.Nr	AIISI	JIS	CHEMICAL COMPOSITION IN %						DELIVERY CONDITION	MANUFACTURING PROGRAMME		USAGE		
						C	S	Ni	Cr	Mo	V		Others	Hardness HB		Thickness range mm inches	Width mm inches
COLD WORK TOOL STEELS		100 Mn Cr W 4	1.2510	01	-	0.90	0.001	-	0.55	-	0.10	W	<212	10-160 0.4-6.3	1000-3000 39.3-118.1		
		50CrMoV13-15	1.2355	S 7	-	0.50	0.001	-	3.25	1.35	0.20	-	<225	10-200 0.4-7.9	1000-2600 39.3-102.3	High toughness, low to medium wear resistance for shear blades and stamping tools (mild steels and medium thicknesses)	
		X 100CrMo V5.1	1.2363	A 2	SKD12	1.00	0.001	-	5.20	0.95	0.20	-	<240	10-120 0.4-4.7	1000-2600 39.3-102.3		
		X 153CrMo V12	1.2379	D 2	SKD 11	1.55	0.001	-	11.75	0.75	0.75	-	<255	15-100 0.59-3.9	1000-2000 39.3-78.7	High wear resistance with limited toughness and chipping resistance. Shear blades, stamping processing of tools (except high strength steels)	
		Tenasteel®	® Registered trademark Patented product				1.00	0.001	-	7.50	2.60	0.30	Ti	<255	8-350 0.3-13.8	500-2100 19.7-82.7	Combining high wear and high chipping resistance. Stamping tools, shear knives to process high strength steels and high thicknesses
HOT WORK TOOL STEELS		X 45 Ni Cr Mo 4	1.2767	-	-	0.45	0.001	3.90	1.30	-	-	-	<260	15-350 0.59-13.8	1000-3000 39.3-82.7	High toughness - Medium softening resistance - Forging tools	
		X 38 Cr Mo V 5.1	1.2343	H 11	SKD 6	0.39	0.001	-	5.15	1.25	0.35	-	<230	15-350 0.59-13.8	1000-2100 39.3-82.7	Good softening resistance for forging dies and dies casting dies (short series)	
		X 40 Cr Mo V 5.1	1.2344	H 13	SKD 61	0.40	0.001	-	5.00	1.30	1.00	-	<230	15-350 0.59-13.8	1000-2100 39.3-82.7		
			1.2347	-	-	0.40	0.10	-	5.25	1.40	0.95	Si : 1	350 - 385	13-75 0.51 - 2.95	2000 78.7		
		Isotrop	~ X 38 Cr Mo V 5.1 mod	1.2343 mod	H 11 mod	~SKD 6	0.36	0.001	-	5.10	1.4	0.35	Si=0.30	<230	100-360 3.9-14.1	1000-2100 39.3-82.7	Improved grades for die casting dies and forging. High toughness, high heat checking resistance NADCA approved material
			55 Ni Cr Mo V 7	1.2714	-	SKT4	0.55	0.001	1.70	1.10	0.50	0.10	-	360-400	15-120 0.59-4.7	1000-2000 39.3-78.7	Holder blocks and dies for closed die forging
	MX01	-	-	-	-	0.19	0.001	1.00	2.00	0.80	0.20	B	360-400	200-500 4-20	2000 78.7	Forging dies for closed die forging with improved life performance	

Other properties can be studied by the mill on request. Industeel reserves the right to modify above data.

Contact Marketing : +33 3 85 80 52 56  
 Contact Sales : +33 4 77 75 21 29  
 Fax : +33 4 77 75 20 01  
<http://industeel.arcelormittal.com>